

FLEXIBLE METAL-CLAD LAMINATE AND
METHOD FOR PRODUCING THE SAME

Abstract of the disclosure:

5

Disclosed are a flexible metal-clad laminate comprising a metal foil and a heat-resistant resin film layer formed on one side of the metal foil, the heat-resistant resin film layer comprising a crosslinked
10 condensation polymer and having an N-methyl-2-pyrrolidone-insoluble content of at least 1%, and a method for producing the flexible metal-clad laminate comprising the steps of applying a heat-resistant resin solution to a metal foil; predrying the metal foil until the heat-
15 resistant resin layer has a residual solvent content of 10 to 40% by weight; and carrying out solvent removal and heat-treatment while controlling the crosslinking reaction of the resin.